



Tena-Film Extreme Pressure Greases

Grades: EP No. 1, EP No. 2

SPECIFICATIONS	EP No. 1	EP No. 2
Worked Penetration @ 77 °F	310/340	265/295
Metallic Soap	None	None
Fillers	None	None
Water, %	0.1	0.1
Free Fatty Acid %	0	0
Alkali %	0	0
Corrosion	Negative	Negative
Dropping Point, ASTM	+ 500 °F	+ 500 °F
Color	Translucent Amber	Translucent Amber
Texture	Smooth-Buttery	Smooth-Buttery
Mineral Oil % Minimum	92	91
Viscosity of Base oil @ 100 °F, SUS	1100	1100
Flash °F, Minimum	575	575
Wheel Bearing Leakage (ASTM D-1263) @ 220 °F	1.0% max.	1.0% max.
ASTM D-1743-60T Bearing Rust Test	Pass	Pass
Oil Separation & Evaporation, 24 hrs. @ 250 °F	2.0% max.	2.0% max.
Timken E.P. Rest – OK Load	40 lbs.	40 lbs.

Baum's Castorine Co., Inc.
Manufacturing Chemists Since 1879